

Grade	Raw Material	Non GMO	Loss on Drying	Solvent content
CCS Regular	wood pulp		max. 10%	max. 1% MeOH
CCS Premium	wood pulp	✓	max. 10%	max. 0.5% EtOH
CCS Premium LM	wood pulp	✓	max. 6%	max. 0.01% EtOH

DETAILS	
Description	White or Greyish-White Powder.
Identification (A, B, C) (1,2,3)	Confirms
Degree of substitution	0.60 to 0.85
Loss on Drying	NMT 10.0%
Ph	5.0-7.0
Content of Water - Soluble Substance	NMT 10.0%
Residue on Ignition / Sulphated Ash	14.0% to 28.0%
Settling volume	10.0 to 30.0 ml
Sodium chloride & sodium glycolate	NMT 0.5%
Heavy Metals	NMT 10 PPM
Iron	NMT 10 PPM
Particle size (% Passes through)	
100 Mesh (CCS - REGULAR)	NLT 98.0%
200 Mesh (CCS - PREMIUM)	NLT 98.0%

MICROBIAL LIMITS	
Total Viable Aerobic Count	N.M.T. 1000cfu/g
Total yeast & Mould Count	N.M.T 100cfu/g
Staphylococcus aureus	Absent
Escherichia Coli	Absent
Pseudomonas aeruginosa	Absent
Salmonella species	Absent